



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>7</sup> :</b> <b>C08F 8/00, C08G 77/38, G02B 1/04</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 00/55212</b> <b>(43) International Publication Date:</b> 21 September 2000 (21.09.00)
<b>(21) International Application Number:</b> PCT/EP00/02539 <b>(22) International Filing Date:</b> 16 March 2000 (16.03.00) <b>(30) Priority Data:</b> 9900935-9                      16 March 1999 (16.03.99)                      SE <b>(71) Applicant (for all designated States except US):</b> PHARMACIA & UPJOHN GRONINGEN BV [NL/NL]; P.O. Box 901, NL-9700 AX Groningen (NL). <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> HODD, Kenneth, A. [GB/GB]; 5 Rackery Hall Mews, Rackery Lane, Caer-Estyn, Wrexham LL12 0PB (GB). DILLINGHAM, Keith, Alfred [GB/NL]; Verlengde Grachtstraat, NL-9717 GG Groningen (NL). <b>(74) Agents:</b> FORSLUND, Niklas et al.; Pharmacia & Upjohn AB, S-112 87 Stockholm (SE).		<b>(81) Designated States:</b> AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
<b>(54) Title:</b> MACROMOLECULAR COMPOUNDS  <b>(57) Abstract</b>  <p>The invention relates to macromolecular photocrosslinkers having polymeric backbones of substituted ethylene or substituted siloxane groups carrying photoactive groups. The photocrosslinkers are capable of producing, when being exposed to light of determined wavelengths above 305 nm, radicals which are retained on the macromolecular photocrosslinkers and reacting so as to accomplish a crosslinked network structure. The invention further relates to the use of the photocrosslinkers in different systems and their utility in production of medical devices including ophthalmic lenses.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

## Macromolecular compounds

### Field of invention

5

The present invention relates to new photoinitiators capable of acting as photocrosslinkers providing a combination of photoinitiating and crosslinking processes.

### Background of invention

10

The UV curing of resin formulations is widely used in industry as the setting process for coatings, adhesives, and more recently paints. Such formulations may comprise a combination of vinyl, usually acrylate, monomers and crosslinkers, together with a photoinitiator. Other possible constituents of the formulations include crosslinkers and  
15 vehicles. In general an advantage of photocurable formulations is that the monomers act as their own vehicle, and the use of solvent is obviated, which has environmental advantages.

Advances in the technology of photocuring, improvements such as, those in UV lamps, cationic initiators for epoxide-based formulations, water borne coatings, and many  
20 novel monomers has enabled this production process to penetrate a number of important manufacturing sectors. Photopolymerization is now used in photoresists for printed circuits and microelectronics, for photolithography, magnetic recording media, glass-fiber laminates, and for medical devices, especially for dental and ophthalmic applications.

For the medical applications of photopolymerisation it is usual to employ visible  
25 light, rather than UV, to effect the cure of the resin formulation. The use of visible, usually blue, light avoids exposing patient and dentist or surgeon to harmful irradiation. Increasingly the merit of this approach is being recognized for industrial practice, where operatives also need protection from prolonged exposure to harmful UV.

European Patent 0800 657 describes a photoinitiator linked to a macromer structure  
30 which together with a copolymerizable monomer and a crosslinker is capable forming a polymerization product, such as an ophthalmic lens that retains photoinitiator radical in

the resulting network. This is advantageous in medical applications wherein such potentially harmful radicals must be carefully controlled. However, this system would not be applicable for producing a polymerized product directly in the capsular bag in the eye since it is not directed to photoinitiators activated by light in the visible range. US Patent  
5 No. 4,536,265 discloses siloxane polyphotoinitiators to be used with a curable silicone resin. This system is UV curable and consequently it will not be applicable for photocuring in the living eye.

It is a characteristic of almost all, if not all, of the formulations used for aforementioned types of application that they are crosslinked. Crosslinking of the  
10 polymeric bases which constitute the coatings or artifacts of the aforementioned industrial products confers important advantages upon them. Crosslinked polymers have greater environmental (e.g. temperature and moisture) resistance, solvent resistance and dimensional and mechanical stability, than equivalent linear polymers. This is especially so for where the equivalent linear polymer are produced by photopolymerisation they  
15 have an atactic, non-crystalline, structure.

Crosslinking is introduced into photopolymerized products by including in the formulation for the resin, coating or gelling system, an acrylate, or similar, crosslinker, which is characterized by having two or more crosslinkable acrylate or vinyl functions. In some formulations this crosslinking species is a polymer of low molecular weight. The  
20 crosslinker copolymerizes with the monomers of the formulation to produce a network structure.

It is the object of the present invention provide compounds which act as photocrosslinkers for vinyl, acrylate and methacrylate monomers and acrylated silicone compositions, especially in solution.

25 It is also an important object of the present invention to provide photocrosslinkers with capability to act in aqueous solutions, especially on water soluble macromolecular particles having functional groups for crosslinking.

It is another object of the present invention to provide photocrosslinkers with enhanced photoactivity (100 % conversion of monomer to polymer in aqueous solution)  
30 which reduces photoinitiator residues to a minimum, especially, vinyl modification of

photoinitiator component and thereby reducing compositional drift, Draize and other environmental hazards.

The invention as presented below will explain how the mentioned objects are met while discussing further obvious advantages.

5

### Description of the invention

The present invention pertains to macromolecular hydrophilic photocrosslinkers having a general formula  $(A)_n(B)_m(C)_p$ , wherein

10

- (i) A, B and C are units of substituted ethylene or siloxane groups in the macromolecular structure;
- (ii) A, B and C are randomly distributed and the unit C carries a photoactive group;
- (iii)  $n = 0-98$  mole %,  $m = 0-98$  mole %,  $n+m = 50-98$  mole % and  $p = 0.5-50$  mole %.

15 When the photoactive groups of units C are exposed to light of determined wavelengths above 305 nm, radicals are generated which are retained on the macromolecular photocrosslinkers and will react to form a crosslinked network structure. Preferably the final structure is solid article.

The photocrosslinker further preferably further comprises functional groups for crosslinking. Such groups are conventionally vinylic, acrylic or methacrylic groups and their nature and introduction on polymeric backbone are well known to persons skilled in the art and will be referred to as "functional groups for crosslinking".

20 According to one aspect of the invention a fluid composition of the photocrosslinker in a suitable amount can be directly crosslinked into the final solid product upon sufficient irradiation. In another aspect the composition for crosslinking into a solid article comprises suitable amounts of the photocrosslinker and a polymer carrying functional groups for crosslinking. The photocrosslinker in such a system will thereby replace the conventional combination of crosslinker and photoinitiator. Applicable polymers with suitable functional can readily be provided with the skilled person for the purpose of crosslinking desired articles. For example it would be

30

conceivable to employ polymers having a sufficiently high refractive index to be acceptable as intraocular lenses. Suitable polymers can be, for example, be found in International Patent Application PCT/EP99/07718. In a still another aspect of the present invention, the photocrosslinkers can be employed in a composition, preferably an aqueous composition further comprising at least one copolymerizable vinylic, acrylic or methacrylic monomer. Such monomers and combinations thereof are well known in the art and will not be described herein in further detail. It is, however, to be understood that the photocrosslinker will replace conventional crosslinking agents and their combination with photoinitiators in such systems.

It is highly preferred that the photoactive groups of the photocrosslinkers comprise a phosphine oxide, in order to generate the necessary radicals for crosslinking from the exposure of visible light. More preferably, the photoactive group is an acyl- or aroyl phosphine oxide.

According to a preferred aspect, the photoactive group is linked to the ethylene groups of units C of the photocrosslinkers by a linking group comprising a phenylene group. Optionally, such a phenylene group is substituted in order to obtain more stability.

According to one embodiment of the invention, the photocrosslinkers comprises substituted ethylene units A, B, C of a macromolecular photocrosslinker in according to:

A =  $-\text{CH}_2-\text{C}(\text{R}^1\text{R}^2)-$ , B =  $-\text{CH}_2-\text{C}(\text{R}^1\text{R}^3)-$ , C =  $-\text{CH}_2-\text{C}(\text{R}^1\text{R}^4)-$ , wherein

$\text{R}^1$  is hydrogen or methyl;

$\text{R}^2$  is  $-\text{CON}(\text{Me})_2$ ,  $-\text{CO}_2\text{CH}_2\text{CH}_2\text{OH}$ ,  $-\text{OCOCH}_3$ ,  $-\text{OCOCH}_2\text{CH}_2\text{Ph}$ ,  $-\text{OH}$  or a lactam group;

$\text{R}^3$  is  $-\text{CON}(\text{Me})_2$ ,  $-\text{CO}_2\text{CH}_2\text{CH}_2\text{OH}$ ,  $-\text{OCOCH}_3$ ,  $-\text{OCOCH}_2\text{CH}_2\text{Ph}$ ,  $-\text{OH}$  or a lactam group when B is  $-\text{CH}_2-\text{C}(\text{R}^1\text{R}^3)-$  with the proviso that  $\text{R}^2$  and  $\text{R}^3$  are not the same; and  $\text{R}^4$  is  $-\text{R}^5\text{C}(\text{O})\text{P}(\text{O})\text{R}^6\text{R}^7$  or  $-\text{R}^5\text{P}(\text{O})\text{R}^6\text{OC}(\text{O})\text{R}^7$ , wherein  $\text{R}^5$ ,  $\text{R}^6$  and  $\text{R}^7$  are selected

among same or different aryl groups comprising phenyl, methylphenyl, dimethylphenyl,

trimethylphenyl, methoxyphenyl, dimethoxyphenyl, trimethoxyphenyl, methylolphenyl, dimethylolphenyl, trimethylolphenyl or styryl radicals, or

In the general formula above, -OH denotes a hydroxyl group, Me a methyl group and Ph is a phenyl group. The lactam group typically is a heterocyclic ring structure of 4 to 7 atoms of which at least one is nitrogen. A suitable such lactam group provides a N-vinyl-pyrrolidone structure as one of units A or B on said ethylenic backbone. It is also to be understood that besides the mentioned substituents functional groups for crosslinking can be added to the macromolecule in accordance with conventional methods.

In one advantageous aspect of this embodiment, the photocrosslinkers,  $R^2$  and  $R^3$  according to above are selected so as to form a water-soluble molecule.

Suitable units A and B in the general formula  $(A)_n(B)_m(C)_p$  are selected among, but not limited to, N-vinylpyrrolidone (NVP), 2-hydroxyethylmethacrylate, N-N-dimethylacrylamide and vinyl acetate. The vinyl acetate referred to preferably will be hydrolyzed conventionally to vinyl alcohol. It is also referred to Table 1 below in the exemplifying part of the description for a number of specific photocrosslinkers based on such units (or co-monomers) and 4-vinylbenzoyl-diphenylphosphine oxide (VBPO) as a photoinitiating group. Accordingly, VBPO units constitute units C in said general formula above. Some especially suitable water soluble, blue light activated photocrosslinkers according to the present invention comprise NVP together with vinyl acetate units, N,N-dimethylacrylamide units alone or together with 2-hydroxyethylethacrylate units, all combined with VBPO units. These photocrosslinkers demonstrate high conversion rate (monomer to polymer) and suitably high stability in aqueous solution. This type of photocrosslinkers can be prepared by conventional radical polymerization.

According to another embodiment, the photocrosslinkers described above with general formula can comprise units A, B and C which are siloxane monomer units having a formula

$-R_aR_bSiO-$ , wherein  $R_a$  and  $R_b$  in units A and B are selected among lower substituted or unsubstituted alkyl groups, aryl groups and arylalkyl groups. Preferably, at least one of  $R_a$  and  $R_b$  is an aryl or arylalkyl group. More preferably  $R_a$  and  $R_b$  is substituted with one or more fluorine atoms. Alkyl groups in this context means a  $C_1$  to  $C_{10}$  alkyl group which is

straight or branched.

According to a preferred aspect of this embodiment the siloxane units comprising substituents in accordance with:

5 A is  $-\text{Si}(\text{R}^1\text{R}^2)-\text{O}-$ , B is  $-\text{Si}(\text{R}^1\text{R}^3)-\text{O}-$  and C is  $-\text{Si}(\text{R}^1\text{R}^4)-\text{O}-$ , wherein

$\text{R}^1$  is C1 to C6 alkyl;  $\text{R}^2$  is C1 to C6 alkyl or phenyl;  $\text{R}^3$  is  $\text{R}^1$ ,  $\text{R}^2$  or C1 to C6 fluoroalkyl;

$\text{R}^4$  is  $-\text{R}^5\text{R}^6\text{C}(\text{O})\text{P}(\text{O})\text{R}^7\text{R}^8$  or  $-\text{R}^5\text{R}^6\text{P}(\text{O})\text{R}^7\text{OC}(\text{O})\text{R}^8$ , wherein  $\text{R}^5$  is a spacing group;  $\text{R}^6$ ,  
 10  $\text{R}^7$  and  $\text{R}^8$  are selected among same or different aryl groups comprising phenyl, methylphenyl, dimethylphenyl, trimethylphenyl, methoxyphenyl, dimethoxyphenyl, trimethoxyphenyl, methylolphenyl, dimethylolphenyl, trimethylolphenyl or styryl radicals.

15 The aliphatic spacing group  $\text{R}^5$  is preferably comprises between one and ten atoms and suitably

The spacing group is  $(-\text{CH}_2)_n$ , wherein n is between 1 and 10.

According to an aspect of the invention particularly suitable for the production of ophthalmic lenses, the photocrosslinkers has radicals connected to the polysiloxane  
 20 backbone such that  $\text{R}^1$  is methyl;  $\text{R}^2$  is methyl or phenyl; and  $\text{R}^3$  is  $\text{R}^1$ ,  $\text{R}^2$  or  $-\text{CH}_2\text{CH}_2\text{CF}_3$ . Such polysiloxane photocrosslinkers may have functional acrylic groups in its terminal ends. Polysiloxanes of this type and their applicability and advantages, especially for injectable intraocular lenses, are disclosed in the International Patent Application PCT/EP99/07781 which document herewith is incorporated as a reference.

25 The present invention further involves a method of forming a macromolecular crosslinked network from a fluid composition comprising photocrosslinkers according to any of the mentioned embodiments by irradiating said composition with light exceeding a wavelength of about 305 nm for a time sufficient to form a solid article. The composition can comprise said

30 photocrosslinkers at least one copolymerizable vinylic, acrylic or methacrylic monomer,



or the composition can comprise a polymer provided with functional vinylic, acrylic or methacrylic groups. It would be obvious to the skilled person to combine any such monomers and polymers together with the inventive photocrosslinkers and also, if found advantageous, combining the composition with a conventional crosslinker suitable for the specifically selected composition. It is further to be understood that the constituents of such a composition shall be selected so as to be sufficiently compatible to each other and the selected fluid environment, for example depending on if photocrosslinkers having ethylene or polysiloxane backbone are selected.

In an especially advantageous application of the method, a medical device or medical implant, such as an ophthalmic lens is produced by means of a conventional molding method wherein the photocrosslinking into a network is a conventional curing process. The inventive method is particularly suitable for producing an intraocular lens by means of injection and subsequent photocrosslinking direct in the capsular bag of eye, from which the natural lens has been surgically removed.

It is also a part of the present invention to provide an ophthalmically acceptable composition comprising the new photocrosslinkers. Such a composition will typically have a refractive index greater than about 1.39 and a viscosity such that said composition can be injected through standard cannula having a needle of 15 Gauge, or finer. Such a composition can further comprise of any suitable constituents as outlined above that can be a part of the network provided by the subsequent photocrosslinking.

The photocrosslinkers according to the present invention provide for a combination of photoinitiating and crosslinking processes. It is an important feature of the present invention to effect this combination of function by attaching photoactive groups to a polymeric or macromolecular structure. The photoactive groups, when exposed to light of the appropriate wavelength, will undergo photoinduced scission and generating radicals, which are retained on the polymeric or macromolecular structure. These retained radicals then initiate, terminate, or, in some other way participate in the gel forming process that is the objective of the radiation cure of the photomaterial. The use of the inventive photocrosslinkers confers distinct advantages, both chemical and environmental, as compared with the combination of a separate photoinitiator and crosslinker. In a chemical

context the use of a photocrosslinker gives opportunities to produce networks that are more homogeneous than those produced by photocuring conventional photocurable systems. The latter systems, involving as they do, combinations of monomers, have structures dependent on the reactivity ratios of the monomers and crosslinkers. Often, for  
5 example, in a coating being manufactured at high rates of production, a crosslinker is selected because of its high reactivity. Disparities in the reactivities of the components of a formulation gives rise to compositional drift, the change of the average unit composition during the course of a polymerization, and this in relation to a reactive crosslinker implies that sections of a network forming later, in the curing process, have a  
10 lower crosslink density than sections formed earlier. Improving the homogeneity of crosslinked networks is a subject receiving greater attention as the technical demands imposed on industrial products increases. Homogeneous networks have, for example, higher fracture toughness and better optical properties heterogeneous networks. The shrinkage occurring during their formation is more uniform allowing for more precision  
15 in castings. The benefits of using a photocrosslinker as a network former, as compared with a combination of photoinitiator and crosslinker, arise because the radical species they produce act as crosslinkers *via* the polymer chain to which they are attached. Further such radicals are generated throughout the setting phase, their concentration being controlled by the photoinitiating species' quantum efficiency and the intensity of the  
20 light, which may be modulated during the setting, in addition to its concentration. This distinction results in the formation of networks having a more controlled and homogeneous structure.

Retaining photoinitiator residues in the network of a medical product, such as a contact lens or a dental filling has desirable physiological implications. Further  
25 photocrosslinkers because of their polymeric, or macromolecular, nature are more acceptable, environmentally, than many conventional crosslinkers which are known to cause skin and lung irritation.

Within the context of the present invention, it is possible to substitute a photocrosslinker, either completely, or partially, for a combination of a conventional  
30 photoinitiator and a conventional crosslinker. Alternatively, the inventive

photocrosslinkers can be used in combination with a conventional photoinitiator or a conventional crosslinker, as will be understood by practitioners skilled in formulating systems for crosslinking.

Persons skilled in this art will also appreciate that the inventive photocrosslinkers as  
5 described herein for photoactive systems responsive to visible light may be applied  
equally to systems responsive to UV light, so the present invention is of very general  
applicability.

**Detailed and exemplifying description of the invention****Example 1**5 **PHOTOCROSSLINKER POLYMER PREPARATIONS**Table 1

photocrosslink ers	VBPO (mole%) 1	Comonomer 1 (mole%)	Comonomer 2 (mole%)
P31-1	3.5	HEMA(5)	NVP(91.5)
P32-1	3.5	VAc(10)	NVP(86.5)
P40-3	4	DMA(96)	none
P40-4	4	PEMA(96)	none
P41-1	6	DMA(94)	none

- 10 The following Examples describe the preparation of P32-1(3), P40-3 & P41-1 (comparison), and P40-4 respectively. In addition examples demonstrating photocrosslinkers of DMA and 4-vinyl-2,6-dimethylbenzoylphosphine oxide are added (Examples 1E and 1F).

15 **Example 1A**

Photocrosslinker Copolymer employing N-Vinylpyrrolidone and Vinyl acetate

- This preparation, on an 8g monomer scale, used monomers in the molar ratio:
- 20 86.5 parts N-vinylpyrrolidone (VP): 10 parts vinyl acetate (Vac): 3.5 parts vinylbenzoyldiphenylphosphine oxide (VBPO).

Methoxydiphenylphosphine, 0.520g, was weighed to a dried 100ml twin-neck flask, with one neck septum sealed, and coated in aluminium foil to exclude light. Toluene, 3 ml, and a magnetic stir bar were added and the flask flushed with dry nitrogen. The stopcock was briefly removed and 4-vinylbenzoyl chloride, 0.409g, added, the flask  
5 being again flushed with dry nitrogen, then placed in a bath at 65°C, with magnetic stirring.

After 15 minutes, the other monomers: VP, 6.620g, and Vac, 0.595g, were diluted with a previously prepared solution of azobisisobutyronitrile (AIBN), 0.080g in 8ml toluene, and the mixture injected to the flask and rinsed in with a further 4ml toluene.  
10 The polymerization mixture was heated at 65°C with magnetic stirring for 8 hours, yielding a clear pale yellow solution, which was precipitated, in subdued light, to diethyl ether. The supernatant was discarded and the pale sludge-like precipitate taken up in 30ml methanol and reprecipitated to ether as a curdy precipitate. The supernatant was decanted, and the polymer product dried to constant weight under vacuum at 35°C .  
15 Yield was 5.751g (72%) of friable pale yellow polymer. Elemental analysis gave 0.65% P, corresponding to 6.9%ww VBPO units (0.209mmol/g), and 10.70% N, corresponding to 84.5%ww VP units, and thus a mean unit mass of 115 Daltons. SEC gave Mn 32,000 , Mw 103,000. This implies a number average chain length of ca.280 units, with ca.7 photoactive units per chain.

20

### Example 1B

#### Photocrosslinker Copolymer employing N-Dimethylacrylamide (I)

25 In this example, 4-vinylbenzoyldiphenylphosphine oxide (VBPO), 4 mol%, was copolymerized with N,N-dimethylacrylamide (DMA), 96 mol%, on a 6g scale.

Methoxydiphenylphosphine, 0.481g, was weighed to a dried 24x150mm Quickfit tube, and 2.5ml dry toluene added. The tube was then wrapped in aluminium foil to exclude light. 4-Vinylbenzoyl chloride, 0.368g, and a magnetic stir bar were added, and  
30 the tube septum sealed, N<sub>2</sub> flushed, and placed in a bath at 65°C with stirring. After 15 minutes a solution of DMA, 5.26g, and AIBN, 0.060g, in toluene, 5ml, was injected by

syringe and rinsed in with a further 3.6ml toluene. The mixture was stirred 6h at 65°C, yielding a viscous orange-yellow solution, which was diluted with methanol and precipitated in diethyl ether. The product was reprecipitated from methanol to ether, and vacuum dessicated at room temperature. Yield, 2.56g (43%) of friable pale yellow  
5 polymer, analysis 0.82% P corresponding to 8.8%ww VBPO units (0.265mmol/g). GPC using poly(ethylene glycol) standards gave Mn 25,000; Mw 100,000 .

### Example 1C

10 Photocrosslinker Copolymer employing N-Dimethylacrylamide (II)

Example 2B was repeated on a 12 g scale, but with monomer ratio 6 mol% VBPO (2.12 g), 94 mol% DMA (9.89 g), with 0.120 g AIBN, 22.3 ml toluene, and polymerization time extended to 8h at 65°C. The yield was 7.17g (60%) of yellow polymer, analysis  
15 1.49% P corresponding to 16.0.%ww VBPO (0.481mmol/g). GPC gave Mn 12 000 and Mw 88000.

### Example 1D

20 Photocrosslinker Copolymer employing 2-Phenylethyl methacrylate

In this example, 4-vinylbenzoyldiphenylphosphine oxide (VBPO), 4 mol%, was copolymerized with 2-phenylethyl methacrylate (PEMA), 96 mol%, on a 6g scale.

Methoxydiphenylphosphine, 0.271g, was weighed to a dried 24x150mm Quickfit  
25 tube, and 2.5ml dry toluene added. The tube was then wrapped in aluminium foil to exclude light. 4-Vinylbenzoyl chloride, 0.204g, and a magnetic stir bar were added, and the tube septum sealed, N<sub>2</sub> flushed, and placed in a bath at 65°C with stirring. After 15 minutes a solution of PEMA, 5.60g, and AIBN, 0.060g, in toluene, 5ml, was injected by syringe and rinsed in with a further 3.6ml toluene. The mixture was stirred 6h at 65°C,  
30 yielding a fairly viscous pale yellow solution, which was diluted with chloroform and precipitated to methanol. The product was reprecipitated from chloroform (with THF

added to clarify the solution), and vacuum dessicated at room temperature. Yield, 4.67g (78%) of friable pale yellow polymer, analysis 0.48% P corresponding to 5.2%ww VBPO units (0.155mmol/g). GPC in THF using polystyrene standards gave Mn 49,300; Mw 108,500 .

5

### Example 1E

In this example, 4-vinyl-2,6-dimethylbenzoyldiphenylphosphine oxide (VDMBPO), 4 mol%, was copolymerized with N,N-dimethylacrylamide (DMA), 96 mol%, on a 12g scale.

Methoxydiphenylphosphine, 0.979g, was weighed to a dried flask and 5ml dry toluene added. The flask was wrapped in aluminium foil to exclude light. 4-Viny-2,6-dimethylbenzoyl chloride, 0.885g, and a magnetic stir bar were added, and the flask septum sealed, N<sub>2</sub> flushed, and placed in a bath at 65°C with stirring. After 15 minutes a solution of DMA, 10.426g, and AIBN, 0.121g, in toluene, 9.3ml, was injected by syringe and rinsed in with a further 8ml toluene. The mixture was stirred 8h at 65°C, yielding a viscous pale yellow solution, which was diluted with 20ml ethanol and precipitated in diethyl ether. The product was reprecipitated from ethanol to hexane, and vacuum dessicated at room temperature. Yield, 8.53g (71%) of friable pale yellow polymer, analysis 0.58% P corresponding to 6.75%ww (1.95mol%) VDMBPO units (0.187meq/g).

The polymer was water soluble and showed excellent hydrolytic stability; tested over the course of a year the product showed no measurable decrease in photoactivity. GPC gave Mn 6,000; Mw 26,000 .

### Example 1F

Example 1E was repeated employing VDMBPO 5 mol and DMA 95 mol%. Yield was 43% of pale yellow polymer, analysis 0.86% P corresponding to 10.0%ww (2.97mol%) VDMBPO units (0.278meq/g). GPC gave Mn 7,000; Mw 32,500.

30

**Example 1G**

Example 1F was repeated employing VDMBPO 5 mol% and DMA 95 mol%. Yield was 55% of pale yellow polymer, analysis 0.73% P corresponding to 8.5%ww (2.49mol%) VDMBPO units (0.236meq/g). GPC gave Mn 5,600; Mw 24,000.

**EXAMPLE 1H**

1,3,5-trimethylbenzoyl-styrylphenylphosphine oxide (TMBSPO), 4 mol%, was copolymerized with N,N-dimethylacrylamide (DMA), 96 mol%, on a 12g scale.

First methoxystyrylphenylphosphine, 0.800g, was weighed to a dried flask and 5ml dry toluene added. The flask was wrapped in aluminium foil to exclude light. 1,3,5-trimethylbenzoyl chloride, 1.061g, and a magnetic stir bar were added, and the flask septum sealed, N<sub>2</sub> flushed, and placed in a bath at 65°C with stirring. After 15 minutes subsequently a solution of DMA, 10.241g in 15 mL of toluene, and AIBN, 0.120g in 5.0 mL of toluene, were injected by syringe. The mixture was stirred 8h at 65°C, yielding a viscous pale yellow solution, which was diluted with 20ml ethanol and precipitated in diethyl ether. The product was reprecipitated from ethanol to diethylether, and vacuum dessicated at room temperature. Yield was 55% of pale yellow polymer, analysis 0.87% P corresponding to 10.4%ww (2.40mol%) TMBSPO units (0.227meq/g). GPC gave Mn 9,000; Mw 35,000.

The experiment was repeated employing TMBSPO 2.5 mol% and DMA 97.5 mol%. Yield was 79% of pale yellow polymer, analysis 0.43% P corresponding to 5.1%ww (1.19mol%) TMBSPO units (0.112meq/g). GPC gave Mn 15,000; Mw 94,000.

Finally, the experiment was repeated employing TMBSPO 4 mol% and PEMA 96 mol%. Yield was 68% of friable pale yellow polymer, analysis 0.56% P corresponding to 5.4%ww TMBSPO units (0.149mmol/g). GPC gave Mn 19,000 and Mw 165,000.



**Example 2**

The following examples refer to photopolymerization including the inventive photocrosslinkers compared with photopolymerization with commercially available  
5 photoinitiators.

**Example 2A**

The state of the art photoinitiator Irgacure 1800 (ex Ciba-Geigy, 10.0 mg) was dissolved,  
10 in subdued light, in 2-hydroxyethylmethacrylate (HEMA, ophthalmic grade ex Polysciences, 970 mg) and 1,6-dihydroxyhexane diacrylate (HDDA, ex, 20.0 mg), and a 10.0 mg sample pipetted into an open DSC aluminum sample pan. The sample pan, covered with a cover-slip of thin glass, was placed in the sample position of the head of a TA Instruments Differential Photocalorimeter (DPC). The temperature of the head was  
15 allowed to stabilize under N<sub>2</sub> at 37°C (or in some cases 23°, and the sample irradiated with blue light at an intensity of 8-9 mWcm<sup>-2</sup>.

The area of the polymerization exotherm was determined by conventional computation and the Jg<sup>-1</sup> of monomer calculated. From the Jg<sup>-1</sup> the percentage conversion of monomer  
20 to polymer was calculated using a literature value for the latent heat of polymerization of the monomer, ΔH<sub>p</sub>. The findings are collected in Table 2.

Using the same composition as was used for the DPC tests discs (2mm thick x 16mm diameter) of polyHEMA were cast in PTFE casting cells. About 500mg of the mixture of  
25 monomers and photoinitiator were introduced into the cell which was closed with a glass slide and irradiated with blue light, either from a blue light dental gun, or from a proprietary light generator (Efes Novacure), for 3min.

**Example 2B**

The method described in Example 2A was repeated using with the state of the art photoinitiator Lucirin TPO (ex BASF, 10.0mg) instead of Irgacure 1800.

5

**Example 2C**

The method described in Example 2A was repeated using HEMA (900.0mg), no HDDA, and, instead of Irgacure 1800, a photocrosslinker according to the present invention (P31-1, see Table 1. for composition, 100.0mg)

10

**Example 2D**

The method described in *Example 2C* was repeated using a photocrosslinker according to the present invention (P32-1, see Table 1. for composition, 100.0mg).

15

**Example 2E**

The method described in *Example 2C* was repeated using a photocrosslinker according to the present invention (P40-3, see Table 1. for composition, 100.0mg).

20

**Example 2F**

The method described in *Example 2C* was repeated using a photocrosslinker according to the present invention (P41-1, see Table 1. for composition, 100.0mg).

25

**Example 2G**

The method described in *Example 2A* was repeated using a photocrosslinker according to the present invention (P32-1, 100.0mg) instead of Irgacure 1800, HEMA (600.0mg),

30

water(300mg) and no HDDA.

#### Example 2H

- 5 As *Example 2G*, using P40-3 (50.0mg) to replace P32-1, and HEMA (500.0mg), water (450.0mg).

#### Example 2I

- 10 As *Example 2H* using P41-1(50.0mg) to replace P40-3.

#### Example 2J

- The method described in *Example 2A* was repeated using 2-phenylethylacrylate (PEA,  
15 990.0mg, ex Polymer & Dajac Laboratories) instead of HEMA and no HDDA.

#### Example 2K

- The method described in *Example 2A* was repeated using instead of Irgacure 1800 a  
20 photocrosslinker (P40-4, see Table 1. for composition, 100.0mg ) and PEA (900mg) but  
no HDDA or HEMA.

- The % conversions of monomer to polymer in Table 2., Examples 2A and 2B, the  
commercial photoinitiators, and the photocrosslinkers, Examples 2C to 2E, are  
25 comparable showing that the photocrosslinkers behave as efficient photoinitiators,  
especially giving regard to the concentrations of photoactive species, the acylphosphine  
oxide (shown in Table 1) Further when these findings are compared with Examples 2G to  
2I the comparison reveals that correctly designed photocrosslinkers (Examples 2H and  
2I) exhibit 100% conversions in solution in water.

For the 2-phenylethylacrylate monomer the photocrosslinker P40-4, based on 2-phenylethylmethacrylate, is also very efficient as a photoinitiator (comparing Examples 2J and 2K) giving 100% conversion of monomer to polymer gel, as judged from the heat of polymerization (based on experimentally determined  $\Delta H_p$ ).

5

Table 2. A comparison of the completeness of blue light photopolymerisation of HEMA, HEMA in water, & PEA using low molecular weight photoinitiators and photocrosslinkers

Ex. No.	Formulation <sup>a</sup> (wt%)[m.eq photoactive ingredient <sup>b</sup> /100g]	Heat of Polym. (Jg <sup>-1</sup> )	Polym. time (min)	Conversion %
2A	HEMA(97)HDDA(2)I1800(1)[0.51 ]	351	3.5	80
2B	HEMA(97)HDDA(2)TPO(1)[2.9]	357	1.5	82
2C	HEMA(90)P31-1(10)[2.0]	308	6	70
2D	HEMA(90)P32-1(10)[2.3]	309	3	71
2E	HEMA(90)P40-3(10)[2.7]	307	2	70
2F	HEMA(90)P41-1(10)[4.8]	361	1.5	82
2G	HEMA(60)H <sub>2</sub> O(30)P32-1(10)[2.3]	>275	>7	>63
2H	HEMA(50)H <sub>2</sub> O(45)P40-3(5)[1.4]	452	7	100(approx.)
2I	HEMA(50)H <sub>2</sub> O(45)P41-1(5)[2.4]	454	6	100(approx.)
2J	PEA(99)I1800(1)[0.51]	455	2.5	100(approx.)
2K	PEA(90)P40-4(10)[1.6]	456	3.5	100(approx.)

10

<sup>a</sup>Photocrosslinkers, and monomer HEMA, as Table 1.: commercial photoinitiators

I1800, bis(2,6-dimethoxybenzoyl)-trimethylpentylphosphine oxide (25%) + 1-hydroxy-cyclohexylphenylketone (75%)(Irgacure 1800 ex Ciba-Geigy)

TPO, 1,3,5-trimethylbenzoyldiphenylphosphine oxide (Lucirin TPO ex BASF):

monomer PEA, 2-phenylethylacrylate: crosslinker HDDA, hexan-1,6-diol diacrylate

5    <sup>b</sup>m.eq. of acylphosphine oxide/100g of formulation.

### Example 3

Examples for Gelation Tests:

10

#### Examples 3A and 3B

Using the formulations described above in Examples 2J and 2K and the casting method described in *Example 2A* discs were prepared.

15

#### Example 3C

Irgacure 2959 (ex Ciba-Geigy, 10.0 mg) was dissolved, in subdued lighting, in 2-hydroxyethylmethacrylate (HEMA, ophthalmic grade ex Polysciences, 550.0 mg) and  
20    water (440.0 mg). Test discs (2mm thick x 16mm diameter) of polymer were cast in PTFE casting cells. About 800mg of the mixture of monomers and photoinitiator were introduced into the cell which was closed with a glass slide and irradiated with light from a proprietary light generator (Efes Novacure), for 3 min.

#### 25    Example 3D

As *Example 3C* with Irgacure 2959 (30.0 mg), HEMA (540.0 mg) and water (430.0 mg).

#### Example 3E

30    As *Example 3C* with P40-3 (100.0 mg) replacing Irgacure 2959, HEMA (500.0mg), and

water (400.0mg).

### Example 3F

- 5 As *Example 3C* with P41-1 (70.0mg) replacing Irgacure 2959, HEMA (510.0mg), and water (420.0mg).

### Example 3G

- 10 As *Example 4C* with P40-4 (50.0mg) replacing Irgacure 1800, PEA (900.0mg), and additional crosslinker, CE7-2 ( 2-phenylethylmethacrylate/2-hydroxy-3-acryloxypropylmethacrylate copolymer [0.9:0.1 mole ratio], 50.0mg).

### Example 3H

- 15 As *Example 3G* with Irgacure 1800 (21.0mg) replacing P40-4, PEA (940.0mg), and crosslinker, CE7-2 ( 2-phenylethylmethacrylate/2-hydroxy-3-acryloxypropylmethacrylate copolymer [0.9:0.1 mole ratio], 60.0mg).

### 20 Example 3I

As *Example 3B* with PEA (750.0mg), and photocrosslinker, P40-4 (250.0mg).

In Table 3. are collected the tests made to check the gelation of the different formulations.

- 25 Where a composition is gelled it does not dissolve in solvent, but swells to an extent related to its crosslink density. Uncrosslinked (sol) polymers dissolve.

- Examples of monomers photopolymerized with conventional photoinitiators of low molecular weight, nos. 4A, 4C and 4D dissolved readily in the appropriate solvent, water  
30 for polyHEMA, and acetone for polyPEA. Example no. 4B showed an intermediate

behavior and dissolved partially in acetone leaving some residual gel. Increasing the proportion of photocrosslinker to 25% (3.9m.eq. of acylphosphine oxide, Example 4I or, adding separate crosslinker, CE7-2 (Example 4G, see below) produced acetone insoluble gel.

5

CE7-2, a polyPEMA which is unsaturated and PEA miscible, being a copolymer of 2-phenylethylmethacrylate/2-hydroxy-3-acryloxypropylmethacrylate [0.9:0.1 mole ratio], was employed as a supplementary crosslinker to the photocrosslinker P40-4, in Examples 4G and 4H. That CE7-2 is an effective cross-linker for photopolymerized PEA is

10 demonstrated in example no. 4H, where in combination with Irgacure 1800 it also yields a gelled product upon irradiation. The products upon irradiation are transparent gelled elastomers of high refractive index ( $RI > 1.54$ ), similar in properties to PEA/PEMA copolymers.

15 Examples 3E and 3F which used photocrosslinkers to replace conventional photoinitiators for HEMA/water compositions were gelled and did not dissolve in water, unlike examples 4D and 4E.

Table 3. Gelation tests on photopolymerized materials, shewing effect of  
20 photocrosslinkers

Ex. No.	Formulation (wt%) <sup>1</sup>	Effect of Solvent	Comments
3A	PEA(99)I1800(1)	Dissolves in Acetone	Not Crosslinked
3B	PEA(90)P40-4(10)	Dissolves & Swells in Acetone	Lightly Crosslinked
3C	HEMA(55)H <sub>2</sub> O(44)I2959 <sup>2</sup> (1)	Dissolves in Water	Not Crosslinked
3D	HEMA(54)H <sub>2</sub> O(43)I2959(3)	Dissolves in Water	Not Crosslinked
3E	HEMA(50)H <sub>2</sub> O(40)P40-3(10)	Swells in Water	Crosslinked Gel

3F	HEMA(51)H <sub>2</sub> O(42)P41-1(7)	Swells in Water	Crosslinked Gel
3G	PEA(90)CE7-2(5)P40-4(5)	Swells in Acetone	Crosslinked Gel
3H	PEA(94)CE7-2(6)I1800(2.1)	Swells in Acetone	Crosslinked Gel
3I	PEA(75)P40-4(25)	Swells in Acetone	Crosslinked Gel

<sup>1</sup> See Tables 1. & 2., and text for an explanation of materials codes

<sup>2</sup> I2959, 2-hydroxy-4'-hydroxyethoxy-2-propiofenone (UV curing)

- 5 The crosslinked structure of the water swollen hydrogels (4E and 4F) was confirmed by stress relaxation tests.

#### Example 4

- 10 The method described in Example 2A was repeated using the following formulations:

##### Formulations (wt %)

- 4A. water (80)/photocrosslinker according Example 1F(20)  
 4B. water (80)/photocrosslinker according Example 1H(20)  
 15 4C. HEMA(45)/water(35)/photocrosslinker according to Example 1C(20)  
 4D. HEMA(45)/water(35)/photocrosslinker according to Example 1F(20)  
 4E. HEMA(45)/water(35)/photocrosslinker according Example 1H(20)  
 4F. HEMA(45)/H<sub>2</sub>O(35)

- 20 The coherent and clear gels resulted from the irradiation of the formulations with blue light, and their relative crosslinked nature was characterized in two ways. The first method was to measure the stress relaxation of the networks, using a Rheometrics RDA-11, and the second method used was to measure the swelling of the gels in water.

- 25 Stress Relaxation Tests-Method



- The RDA-11 was set up with the 16mm gelled sample damped between parallel plates of 25 mm, heated to 35°C, and a strain of 30% applied. During the test the instrument measures the instantaneous stress necessary to maintain 35%, and plots the instantaneous shear modulus ( $G_i$ ) against  $\log t$ . In Table 3, the percentage reductions in the modulus  $G_i$  for the formulations 4A to 4F between  $i = 10$  and 100 s are compared as  $(G(10) - G(100)/G(10)) \times 100$  both before and after swelling in water. The results confirm that the photocrosslinked gel possess coherent network structures.

10.

Table 3. Average Stress Relaxations of Photocrosslinked Formulations 4A to 4F, measured at 35°C

Average stress relaxation	4A	4B	4C	4D	4E	4F
Before swelling-disc1	No result		4.9	3.4	No result	Not measurable
Before swelling-disc2	9.3		15.5	10.9	29.4	
After swelling-disc1			21.4	17.4		
After swelling-disc2	19.1		19.0	13.0	12.4	Not measurable

#### 15 Swelling Test Method

Samples discs from formulations 4A through 4F were weighed, immersed in water for 24 hours at 20°C, dried, and reweighed. Table 4 compares the water absorbed by each formulation on a percentage basis.

20

Table 4.

Percentage water absorbed at 25°C by photocrosslinked gels

Water absorbed (wt %)	4A	4B	4C	4D	4E	4F
Disc1			222	191		Not measurable
Disc2	130	219	230	172	255	Not measurable

5

It was observed that upon irradiation with blue light, the formulation prepared without a crosslinker (4F) did not gel and that no discs suitable for any measurements were formed. Satisfactory discs were prepared from other formulations and stress relaxation results and the water absorption results were in agreement with the sequence: most highly crosslinked 4A>4C<4E least highly crosslinked.

10

**Claims**

1. Macromolecular photocrosslinkers having a general formula

$(A)_n(B)_m(C)_p$ , wherein

- (i) A, B and C are units of substituted ethylene or siloxane groups in the macromolecular structure;
- (ii) C carries a photoactive groups;
- (iii)  $n = 0-98$  mole %,  $m = 0-98$  mole %,  $n+m = 50-98$  mole % and  $p = 0.5-50$  mole %;

and when said photoactive groups are exposed to light of determined wavelengths above 305 nm, radicals are generated and retained on the macromolecular photocrosslinkers and reacting so as to accomplish a crosslinked network structure.

2. Photocrosslinkers according to claim 1 characterized in that said photoactive group comprises a phosphine oxide.

3. Photocrosslinkers according to claim 2 characterized in that the photoactive group is an acyl- or aroyl phosphine oxide.

4. Photocrosslinkers according to claim 3 characterized in that the photoactive group is linked to the ethylene groups of units C by a linking group comprising a phenylene group, said phenylene group being optionally substituted.

5. Photocrosslinkers according to claim 1, wherein the ethylene units A, B, C of the macromolecular structure comprises substituents in accordance with:

$A = -CH_2-C(R^1R^2)-$ ,  $B = -CH_2-C(R^1R^3)-$ ,  $C = -CH_2-C(R^1R^4)-$ , wherein

$R^1$  is hydrogen or methyl;

$R^2$  is  $-\text{CON}(\text{Me})_2$ ,  $-\text{CO}_2\text{CH}_2\text{CH}_2\text{OH}$ ,  $-\text{OCOCH}_3$ ,  $-\text{OCOCH}_2\text{CH}_2\text{Ph}$ ,  $-\text{OH}$  or a lactam group;

$R^3$  is  $-\text{CON}(\text{Me})_2$ ,  $-\text{CO}_2\text{CH}_2\text{CH}_2\text{OH}$ ,  $-\text{OCOCH}_3$ ,  $-\text{OCOCH}_2\text{CH}_2\text{Ph}$ ,  $-\text{OH}$  or a lactam group when B is  $-\text{CH}_2-\text{C}(\text{R}^1\text{R}^3)-$  with the proviso that  $R^2$  and  $R^3$  are not the same unless  $R^2$  and  $R^3$  is  $-\text{OH}$ ; and

$R^4$  is  $-\text{R}^5\text{C}(\text{O})\text{P}(\text{O})\text{R}^6\text{R}^7$  or  $-\text{R}^5\text{P}(\text{O})\text{R}^6\text{OC}(\text{O})\text{R}^7$ , wherein  $R^5$ ,  $R^6$  and  $R^7$  are selected among same or different aryl groups comprising phenyl, methylphenyl, dimethylphenyl, trimethylphenyl, methoxyphenyl, dimethoxyphenyl, trimethoxyphenyl, methylolphenyl, dimethylolphenyl, trimethylolphenyl or styryl radicals.

6. Photocrosslinkers according to claim 5, wherein  $R^2$  and  $R^3$  are selected so as to form a water-soluble molecule.

7. Photocrosslinkers according to claim 5, wherein said lactam units together with units A or B constitute N-vinylpyrrolidone units.

8. Photocrosslinkers according to claim 5, wherein at least one of  $R^2$  and  $R^3$  is hydroxyl.

9. Photocrosslinkers according to claim 5, wherein A is N-vinylpyrrolidone, B is vinyl alcohol.

10. Photocrosslinkers according to claim 1 or 5 provided with functional groups for crosslinking.

11. Photocrosslinkers according to claim 10 provided with functional groups selected among vinylic, acrylic and methacrylic groups.

12. Photocrosslinkers according to claim 1 characterized in that units A, B and C are

siloxane monomer units of a general formula  $-R_aR_bSiO-$ , wherein  $R_a$  and  $R_b$  in units A and B are selected among lower substituted or unsubstituted alkyl groups, aryl groups and arylalkyl groups.

13. Photocrosslinkers according to claim 12, wherein at least one of  $R_a$  and  $R_b$  is an aryl or arylalkyl group.

14. Photocrosslinkers according to claim 13, wherein at least one of  $R_a$  and  $R_b$  is substituted with one or more fluorine atoms.

15. Photocrosslinkers according to claim 1, wherein units A, B, C are siloxane units comprising substituents in accordance with:

A is  $-Si(R^1R^2)-O-$ , B is  $-Si(R^1R^3)-O-$  and C is  $-Si(R^1R^4)-O-$ , wherein

$R^1$  is C1 to C6 alkyl;  $R^2$  is C1 to C6 alkyl or phenyl;  $R^3$  is  $R^1$ ,  $R^2$  or C1 to C6 fluoroalkyl;

$R^4$  is  $-R^5R^6C(O)P(O)R^7R^8$  or  $-R^5R^6P(O)R^7OC(O)R^8$ , wherein  $R^5$  is a spacing group;  $R^6$ ,  $R^7$  and  $R^8$  are selected among same or different aryl groups comprising phenyl, methylphenyl, dimethylphenyl, trimethylphenyl, methoxyphenyl, dimethoxyphenyl, trimethoxyphenyl, methylolphenyl, dimethylolphenyl, trimethylolphenyl or styryl radicals.

16. Photocrosslinkers according to claim 15, wherein  $R^5$  is aliphatic spacing group comprising between one and ten atoms.

17. Photocrosslinker according to claim 16, wherein said spacing group is  $(-CH_2)_n$ , wherein n is between 1 and 10.

18. Photocrosslinkers according to claim 15, wherein  $R^1$  is methyl;  $R^2$  is methyl or phenyl;  $R^3$  is  $R^1$ ,  $R^2$  or  $-CH_2CH_2CF_3$ .

19. Photocrosslinkers according to claim 15 having functional acrylic groups in its terminal ends.
20. A method of forming a macromolecular crosslinked network from a composition comprising a photocrosslinker according to any of claims 1 to 19 by irradiating said composition with light exceeding a wavelength of about 305 nm for a time sufficient to form a solid article.
21. A method forming a macromolecular crosslinked network from a composition comprising a photocrosslinker according to any of claims 1 to 11 and at least one copolymerizable vinylic, acrylic or methacrylic monomer.
22. A method according to claim 20, wherein said composition further comprises a polymer provided with functional vinylic, acrylic or methacrylic groups.
23. A method according to claim 22, wherein said polymer has a backbone of ethylene units.
24. A method according to claim 22, wherein said polymer is a polysiloxane.
25. A method according to any of claims 20 to 24, wherein an ophthalmic lens is produced.
26. A method according to claim 25, wherein an intraocular lens is produced in the capsular bag of the eye.
27. An ophthalmically acceptable composition comprising photocrosslinkers according to any of claims 1 to 19, having a refractive index greater than about 1.39 and a viscosity such that said composition can be injected through standard cannula having a needle of 15 Gauge, or finer.

28. The use of photocrosslinkers according to any of claims 1 to 19 in an ophthalmologically acceptable composition for injection into the capsular bag of the eye.

# INTERNATIONAL SEARCH REPORT

Int. Patent Application No

PCT/EP 00/02539

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08F8/00 C08G77/38 G02B1/04

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08F C08G G02B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	L. ANGIOLINI: "POLYMERIC PHOTOINITIATORS BEARING SIDE-CHAIN BENZOYLDIPHENYLPHOSPHINOXIDE MOIETIES FOR UV CURABLE COATINGS" JOURNAL OF APPLIED POLYMER SCIENCE, vol. 51, no. 1, 3 January 1994 (1994-01-03), pages 133-143, XP000464122 NEW YORK, US page 133 -page 143	1-14
Y	WO 92 09644 A (BAUSCH & LOMB INC.) 11 June 1992 (1992-06-11) page 6, line 1 - line 21; claims 1-30	1-32
Y	WO 92 07885 A (BIOCOMPATIBLES LTD.) 14 May 1992 (1992-05-14) claims 1-16	1-32
	-/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

4 August 2000

Date of mailing of the international search report

16/08/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Permentier, W



## INTERNATIONAL SEARCH REPORT

Int. Application No.

PCT/EP 00/02539

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 5 661 195 A (R. CHRIST) 26 August 1997 (1997-08-26) column 7, line 17 - line 34; claims 1-14	1-32
Y	WO 99 08135 A (ALCON LABORATORIES, INC.) 18 February 1999 (1999-02-18) page 4, line 5 - line 14 page 5, line 4 - line 30 page 6, line 2 - line 14 page 7, line 7 - line 21 page 7, line 32 - page 8, line 7 page 9, line 10 - line 25; claims 1-15	1-32
A	WO 99 08136 A (ALCON LABORATORIES, INC.) 18 February 1999 (1999-02-18) claims 1-20	1
A	DE 17 95 565 A (TONDEO-WERK ADOLF NOSS) 27 January 1972 (1972-01-27) the whole document	15
A	WO 96 31547 A (CIBA-GEIGY AG) 10 October 1996 (1996-10-10) claims 1-32	15
A	US 4 872 877 A (J. TIFFANY) 10 October 1989 (1989-10-10) the whole document	15
A	EP 0 611 786 A (F. HOFFMANN-LA-ROCHE AG) 24 August 1994 (1994-08-24) page 2, line 44 - line 54; claims 1-6	1,15

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 00/02539

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9209644	A	11-06-1992	US 5219965 A	15-06-1993
			AT 144996 T	15-11-1996
			BR 9107041 A	28-09-1993
			CA 2095045 A	28-05-1992
			CN 1061785 A,B	10-06-1992
			DE 69123059 D	12-12-1996
			DE 69123059 T	05-06-1997
			EP 0559809 A	15-09-1993
			ES 2096067 T	01-03-1997
			HK 1006464 A	26-02-1999
			JP 6503373 T	14-04-1994
			KR 184239 B	15-05-1999
			US 5364918 A	15-11-1994
			US 5525691 A	11-06-1996
WO 9207885	A	14-05-1992	AT 146488 T	15-01-1997
			DE 69123756 D	30-01-1997
			DE 69123756 T	03-04-1997
			DK 555295 T	16-06-1997
			EP 0555295 A	18-08-1993
			ES 2094824 T	01-02-1997
			GR 3022397 T	30-04-1997
			HK 53297 A	02-05-1997
			JP 3009356 B	14-02-2000
			JP 9020814 A	21-01-1997
			JP 2593993 B	26-03-1997
			JP 6502200 T	10-03-1994
			SG 43188 A	17-10-1997
US 5661195	A	26-08-1997	US 5494946 A	27-02-1996
			US 5376694 A	27-12-1994
			US 5236970 A	17-08-1993
			US 5869549 A	09-02-1999
WO 9908135	A	18-02-1999	US 6015842 A	18-01-2000
			AU 8396398 A	01-03-1999
			EP 1002243 A	24-05-2000
WO 9908136	A	18-02-1999	US 5891931 A	06-04-1999
			AU 8396498 A	01-03-1999
			CN 1251174 T	19-04-2000
			EP 1002244 A	24-05-2000
DE 1795565	A	27-01-1972	NONE	
WO 9631547	A	10-10-1996	AU 5147796 A	23-10-1996
			CA 2215144 A	10-10-1996
			EP 0819140 A	21-01-1998
			JP 11503183 T	23-03-1999
			NO 974582 A	12-11-1997
			ZA 9602661 A	04-10-1996
US 4872877	A	10-10-1989	US 4872878 A	10-10-1989
EP 611786	A	24-08-1994	CN 1096807 A	28-12-1994
			CN 1091458 A,B	31-08-1994
			DE 59403063 D	17-07-1997
			DE 59408097 D	20-05-1999

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 00/02539

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 611786 A		EP 0611981 A	24-08-1994
		HK 1007196 A	01-04-1999
		JP 2543666 B	16-10-1996
		JP 6289374 A	18-10-1994
		JP 6287453 A	11-10-1994
		US RE36625 E	21-03-2000
		US 5539074 A	23-07-1996
		US 5602661 A	11-02-1997